

**AMENDMENT NO. 2 MARCH 2017
TO
IS 4031 (PART 2) : 1999 METHODS OF PHYSICAL TESTS
FOR HYDRAULIC CEMENT**

**PART 2 DETERMINATION OF FINENESS BY BLAINE AIR
PERMEABILITY METHOD**

(Second Revision)

(Page 1, clause 4.8) — Substitute the following for the existing clause:

‘4.8 NCB Certified Reference Material

1001A shall be used as the reference cement for determination of apparatus constant.

NOTE — ‘NCB CRM-1001A’ may be obtained from:

Centre for Quality Management, Standards & Calibration Services
National Council for Cement and Building Materials
34 Km Stone, NH-2, Delhi Mathura Road
Ballabgarh – 121007 (Haryana)’

(Page 3, clause 5.4.2, first sentence) — Substitute the following for the existing sentence:

‘From a supply of reference cement (NCB CRM – 1001A) of known specific surface, prepare a compacted cement bed and measure its permeability by the procedures given in 5.2.2 to 5.2.4 and 5.3.2.’